

# FR Certificates

| TEST METHOD                       | COUNTRY       | UPHOLSTERY | CURTAINS | BED COVERS | SUFFIX | EXTRA FR BACK COATING | SOAKING | FR FOAM | FOAM TYPE                | FR INT. |
|-----------------------------------|---------------|------------|----------|------------|--------|-----------------------|---------|---------|--------------------------|---------|
| EN1021 PART 1                     | EUROPE        | ●          |          |            | .11    | NO                    | YES     | YES     | 36kg/m <sup>3</sup>      | NO      |
| EN1021 PART 2                     | EUROPE        | ●          |          |            | .11    | NO                    | NO      | YES     | 36kg/m <sup>3</sup>      | NO      |
| EN13773 (CLASS 1)                 | EUROPE        |            | ●        |            | .11    | NO                    | NO      | NO      |                          | NO      |
| NFP 92-503-507 (M1)               | FRANCE        | ●          | ●        |            | .11    | NO                    | NO      | NO      |                          | NO      |
| DIN 4102 (B1)                     | GERMANY       | ●          | ●        |            | .11    | NO                    | NO      | NO      |                          | NO      |
| UNI 9175 (Classe Uno)             | ITALY         | ●          |          |            | .11    | NO                    | YES     | YES     | 30kg/m <sup>3</sup> 75mm | NO      |
| UNI 9177, 9174, 8456 (Classe Uno) | ITALY         |            | ●        |            | .11    | NO                    | YES     | NO      |                          | NO      |
| BS5852 source 0 (cigarette)       | UK            | ●          |          |            | .11    | NO                    | YES     | NO      | 21kg/m <sup>3</sup> 75mm | NO      |
| BS5852 source 1 (match)           | UK            | ●          |          |            | .33    | YES                   | YES     | NO      | 21kg/m <sup>3</sup> 75mm | NO      |
| BS5852 source 5 (CRIB 5)          | UK            | ●          |          |            | .33    | YES                   | YES     | YES     | 40kg/m <sup>3</sup> 75mm | YES     |
|                                   |               |            |          |            | .11    | NO                    | YES     | YES     | 50kg/m <sup>3</sup> 75mm | NO      |
| BS5867 part 2 type B              | UK            |            | ●        |            | .11    | NO                    | YES     | NO      |                          | NO      |
| BS7175 SECTION 3 IGN 0,1 and 5    | UK            |            |          | ●          | .11    | NO                    | NO      | NO      |                          | NO      |
| NFA701                            | USA           |            | ●        |            | .11    | NO                    | NO      | NO      |                          | NO      |
| NFPA260                           | USA           | ●          |          |            | .11    | NO                    | NO      | NO      |                          | NO      |
| CAL117                            | USA           | ●          |          |            | .11    | NO                    | NO      | NO      |                          | NO      |
| IMO-2010 FTP Code Annex 1 Part 7  | INTERNATIONAL |            | ●        |            | .11    | NO                    | NO      | NO      |                          | NO      |
| IMO-2010 FTP Code Annex 1 Part 8  | INTERNATIONAL | ●          |          |            | .11    | NO                    | NO      | YES     | 36kg/m <sup>3</sup>      | NO      |

# Sound Absorption

| TEST METHOD:ISO 354 | RESULTS      |            |
|---------------------|--------------|------------|
| DIN EN ISO 354      | NRC = 0.60   | SAA = 0.59 |
| ISO 11654           | aw = 0.55(H) | class: D   |